MONO ST. ASTIER - one coat render

See: COLOUR CHART

A ready mixed mortar based on Natural Hydraulic lime specially formulated to achieve excellent waterproofing, low capillarity, high breathability, elasticity and vibrant coloured finishes. Substantial savings in cost of painting and maintenance are achievable.

Technical data		Test std. CSTB & EN998.1
Dry Density(hardened product)	1650g.l +/100g/l	Meruc M 4
Elasticity moduli 28days	Between 5000 and 10000 MPa	Meruc E 3
Compressive strength 28 days	Between 4 and 5 N/mm ²	
Flexural strength 28days	Between 2 and 2.5 N/mm ²	MerucR 4
Water retention (on paste)	Between 86% and 94% (± 2%)	MerucU 4
Vapour permeability	$0.5 g x m^2 x h x mmHg$	EN 1015-19
Capillarity	Below 1 g/dm ² .min1/2	Meruc C 1
Fire resistance	Class A (all uses)	
Granulometry:	TF 0-1.3 mm F 0-1.8 mm M 0-2.5 mm G 0-4.0 mm	

Packing: in 30 kg. bags / 49 bags per pallet (1.47T) **Colour Range:** please ask your St. Astier distributor.

Storage/shelf life: in dry store, up to 12 months from production

date. Reseal opened bags a.s.a.p.

Consumption: 1.7/1.8 kg. per mm of thickness per m².

Mortar preparation: add between 4.5 and 5.5 (max) litres of clean

water per bag of 30 kg.

Mix between 5 and 10 minutes max.



See: COLOUR CHART

Application recommendations: on properly prepared background offering adequate keying, cast on or spray on up to 10 mm in one pass for floated finishes or 15 mm if a scratched finish is required. On waterproofed or smooth backgrounds spray or cast on a 1st bonding coat of about 3 mm adding 500 grams of SBR per bag of product. Straighten the work immediately after with an appropriate tool. Float (sponge, wooden or plastic) after 2-3 hours or more depending on weather conditions. **Not suitable for light weight, porous cement blocks.**

Do not work in temperatures below 5°C or above 30°C. Protect fresh mortar from rain, frost or strong drying wind. In hot weather, dampen the background adequately and cure the work by applying a light water mist several times for a period of 72 hours.

The above details are given for general information purposes and do not constitute a specification.

For further Guidance, contact your St Astier Distributor.

Copyright © Setra Marketing Ltd. 2006

